


REFRACTORY MORTAR

BIKMOR 2000R



Product description

- Premixed dry mortar based on refractory cement, silica sand and chemical additives that improve its plasticity, density, water retention properties, etc.

Applications

- Building bar-barbecues, chimneys, ovens, etc.

Precautions

- Check that the product to be used is suitable for the type of support and the type of work that is going to be carried out.
- Always mix the product using the recommended amount of water (approximately 5 liters/sack), and do not add cement, sand or any other product that will modify the original formula.
- Once the life cycle of the paste has been exceeded, do not add water to re-mix.
- The ambient temperature during the application of the product must be between 5° C and 35° C.
- A minimum of 7 days shall be waited prior to progressively applying heat.
- Avoid breathing the powder and contact of the mixed product with the skin and the eyes. For more information consult the applicable Safety Data Sheet.

Technical characteristics

- **Powder density:**.....1.7±0.1 (gr/cm³)
- **Bulk density of fresh mortar (UNE-EN 1015-6):**.....
ō ō ō ō ō ō ō ō ō ō ō ō ō ō ō ō .1.7 ± 0.1 (gr/cm³)
- **Bulk density of hardened mortar (UNE-EN 1015-10):**
..... 1.6 ± 0.1 (gr/cm³)
- **Water % (consistency 175±10 mm UNE-EN 1015-3):**
.....19-21%
- **Compressive strength (UNE-EN 1015-11):**
..... 8 (N/mm²)
- **Theoretical yield:** Approx. 620 (l/ton)
- **Reaction to fire (Decision 96/603/CE):**..... A1
- **Tariff heading**..... 3824.50.90.00

Usage instructions

- Add water and mix manually or mechanically until a homogeneous consistency is achieved.
- To facilitate a good adherence of the product to the support and a proper curing, dry or highly absorbent parts must be slightly moistened.
- Avoid freezing temperatures, strong winds and exposure to intense sunlight. Never use on frozen surfaces.
- In humid environments and on supports with a low absorption rate, the setting time is extended. In very dry weather the setting time is shortened.

Supply

- In 25 kg paper sacks Palletized in 60 sacks/pallet (1500 Kg).
- The supply will follow the General Terms of the Contract that is in force.

Storage

- Storing in sacks guarantees that the characteristics of the product are maintained intact for one year from the manufacturing date, as long as they are kept in a location that is under cover and dry.

Customer / technical service

- In case of doubt regarding the selection, use or application of the products, first consult with our Customer/Technical Service Department.
- If you need a specific product, our Customer/Technical Service Department will help you determine your specific needs and will provide the best solution for your needs.

Remarks

- *Our technical advice, whether the advice is provided verbally or via tests, is provided according to the best of our knowledge but shall be considered only as a recommendation WITHOUT OBLIGATION. Since we are not involved in the execution of the works, the information is provided for general purposes and is not legally binding for BIKAIN.*
- *The technical sheet cannot include all the applications and factors involved with using a material. Therefore, regarding installations not described in this sheet, we recommend consulting with our technical department or carrying out a preliminary test to check the suitability of said application.*
- *The usage instructions are drafted based on our tests and knowledge and do not relieve the consumer from examining or checking the products are suitable for use. Therefore prior to using the product, whomever is going to use it must determine if it is suitable or not for the intended use, since he or she will assume any responsibility that may be derived from its use. The responsibility of BIKAIN shall be limited to the value of the used merchandise.*
- *BIKAIN, a registered company in accordance with Standard UNE-EN-ISO 9001 regarding quality systems, guarantees that its products have been controlled by its quality laboratory in accordance with the characteristics described in the Technical Sheets.*

July 2020

MORTEROS Y REVOCOS BIKAIN, S.A.

Aldebarrena, 18 – 48212 Mañaria (Bizkaia)

+34 946 202 496

www.bikain.com

info@bikain.com

